

Product data sheet

HDPE-regranulate PM HD 045

transparent-white

PROPERTY	VALUE	UNIT	TEST METHOD
Grade	HDPE regranulate	----	----
Origin	post industry	----	----
Color	transparent-white	----	----
Melt flow rate	1,7 - 2,2	g/10min	(190°C/5kg)
Melt flow rate	0,45 – 0,57	g/10min	(190°C/2,16kg)
Density	0,95 - 0,96	g/m ³	(DIN 43479 Verf. A)
Filler (TiO ₂)	3,5	%	----

Moers, 01.05.2019